Durom/Durom Total Resurfacing Hip Investigation

Note: This analysis compares the Durom/Durom head/acetabular combination with all other total resurfacing hip prostheses.

This combination has been identified as having a significantly higher rate of revision. For a detailed explanation of the process used by the Registry that results in identification of prostheses that have a higher than anticipated rate of revision please refer to the Prostheses with Higher than Anticipated Rates of Revision chapter of the most recent AOANJRR Annual Report, https://aoanjrr.sahmri.com/annual-reports-2024.

Note: Procedures using prostheses with no recorded use in 2023 are excluded from the comparator.

TABLE 1

Revision Rate of Primary Total Resurfacing Hip Replacement

The revision rate of the Durom/Durom total resurfacing hip combination is compared to all other total resurfacing hip prostheses.

Table 1: Revision Rates of Primary Total Resurfacing Hip Replacement

Component	N Revised	N Total	Obs. Years	Revisions/100 Obs. Yrs (95% CI)
Durom/Durom	121	847	12919	0.94 (0.78, 1.12)
Other Total Resurfacing Hip	1245	15869	201458	0.62 (0.58, 0.65)
TOTAL	1366	16716	214377	0.64 (0.60, 0.67)

Yearly Cumulative Percent Revision of Primary Total Resurfacing Hip Replacement

The yearly cumulative percent revision of the Durom/Durom total resurfacing hip combination is compared to all other total resurfacing hip prostheses.

Table 2: Yearly Cumulative Percent Revision of Primary Total Resurfacing Hip Replacement

CPR	1 Yr	2 Yrs	3 Yrs	4 Yrs	5 Yrs	6 Yrs	7 Yrs	8 Yrs
Durom/Durom	3.3 (2.3, 4.8) 4	.7 (3.5, 6.4) 5	.6 (4.2, 7.3) 6	.5 (5.0, 8.4) 7	.7 (6.1, 9.7)	8.4 (6.7, 10.5)	8.9 (7.2, 11.0)	9.8 (7.9, 12.0)
Other Total Resurfacing Hip	1.4 (1.2, 1.5) 1	.9 (1.7, 2.1) 2	.3 (2.1, 2.5) 2	.7 (2.5, 3.0) 3	.2 (2.9, 3.5)	3.8 (3.5, 4.1)	4.4 (4.1, 4.7)	4.9 (4.6, 5.3)

CPR	9 Yrs	10 Yrs	11 Yrs	12 Yrs	13 Yrs	14 Yrs	15 Yrs	16 Yrs
Durom/Durom	10.4 (8.5, 12.6)	11.0 (9.0, 13.3)	11.2 (9.3, 13.6)	11.8 (9.8, 14.2)	12.5 (10.4, 14.9)	12.8 (10.7, 15.3)	13.4 (11.3, 15.9)	13.9 (11.7, 16.4)
Other Total Resurfacing Hip	5.4 (5.1, 5.8) 6	5.2 (5.8, 6.6)	5.7 (6.3, 7.1) 7	7.2 (6.8, 7.7)	7.9 (7.4, 8.4)	8.4 (7.9, 8.9)	9.0 (8.5, 9.5)	9.5 (9.0, 10.0)

CPR	17 Yrs	18 Yrs	19 Yrs	20 Yrs	21 Yrs	22 Yrs	23 Yrs
Durom/Durom	15.0 (12.7, 17.7)	15.2 (12.8, 17.9)	15.2 (12.8, 17.9)				
Other Total Resurfacing Hip	10.0 (9.4, 10.6)	10.4 (9.8, 11.0)	10.7 (10.1, 11.4)	11.2 (10.6, 11.9)	11.6 (11.0, 12.4)	12.0 (11.2, 12.7)	12.2 (11.3, 13.1)


FIGURE 1

Yearly Cumulative Percent Revision of Primary Total Resurfacing Hip Replacement

The yearly cumulative percent revision of the Durom/Durom total resurfacing hip combination is compared to all other total resurfacing hip prostheses. In addition, hazard ratios are reported.

Hazard ratios are reported for specific time periods during which the hazard ratio is constant. This is done to enable more specific and valid comparisons of the risk of revision over time. The pattern of variation in risk has important implications with respect to the underlying reasons for any difference.

Figure 1: Cumulative Percent Revision of Primary Total Resurfacing Hip Replacement



Primary Diagnosis for Revised Primary Total Resurfacing Hip Replacement

This table identifies the diagnosis of the primary procedure which was subsequently revised. This information is provided as there is a variation on outcome depending on the primary diagnosis. It is therefore important when considering the reasons for a higher than anticipated rate of revision that there is identification of the primary diagnosis. This information should be compared to the primary diagnosis for the revisions of all other total resurfacing hip prostheses.

Table 3: Primary Diagnosis for Revised Primary Total Resurfacing Hip Replacement

	Durom/Durom		Other Total Re	esurfacing Hip
Primary Diagnosis	Number	Percent	Number	Percent
Osteoarthritis	114	94.2	1141	91.6
Developmental Dysplasia	3	2.5	50	4.0
Osteonecrosis	2	1.7	37	3.0
Other Inflammatory Arthritis	1	0.8	10	0.8
Rheumatoid Arthritis	1	0.8	6	0.5
Other			1	0.1
TOTAL	121	100.0	1245	100.0

Reasons for Revision

This is reported in two ways: a percentage of primary procedures revised and as a percentage of all revision procedures.

% Primaries Revised: This shows the proportional contribution of each revision diagnosis as a percentage of the total number of primary procedures. This percentage can be used to approximate the risk of being revised for that diagnosis. Differing percentages between groups, with the same distribution of follow up time, may identify problems of concern.

% Revisions: The number of revisions for each diagnosis is expressed as a percentage of the total number of revisions. This shows the distribution of reasons for revision within a group but cannot be used as a comparison between groups.

Table 4: Primary Total Resurfacing Hip Replacement - Reason for Revision (Follow-up Limited to 20.5 Years)

		Durom/Durom Other Total Resurfacing Hi			д Нір	
Revision Diagnosis	Number	% Primaries Revised	% Revisions	Number	% Primaries Revised	% Revisions
Loosening	31	3.7	25.6	327	2.1	26.5
Metal Related Pathology	14	1.7	11.6	263	1.7	21.3
Fracture	30	3.5	24.8	240	1.5	19.4
Lysis	10	1.2	8.3	132	0.8	10.7
Infection	12	1.4	9.9	83	0.5	6.7
Pain	12	1.4	9.9	71	0.4	5.7
Prosthesis Dislocation/Instability	2	0.2	1.7	32	0.2	2.6
Osteonecrosis	4	0.5	3.3	29	0.2	2.3
Malposition	1	0.1	8.0	19	0.1	1.5
Tumour				6	0.0	0.5
Progression Of Disease				4	0.0	0.3
Wear Acetabulum				3	0.0	0.2
Implant Breakage Acetabular				2	0.0	0.2
Leg Length Discrepancy				2	0.0	0.2
Heterotopic Bone				1	0.0	0.1
Implant Breakage Head	1	0.1	0.8			
Implant Breakage Stem	1	0.1	0.8	1	0.0	0.1
Incorrect Sizing				1	0.0	0.1
Synovitis	1	0.1	8.0	1	0.0	0.1
Other	2	0.2	1.7	18	0.1	1.5
N Revision	121	14.3	100.0	1235	7.8	100.0
N Primary	847			15869		


Note: This table is restricted to revisions within 20.5 years for all groups to allow a time-matched comparison of revisions. Note: Prostheses no longer used in 2023 are excluded from the comparator.

FIGURE 2

Cumulative Incidence Revision Diagnosis of Primary Total Resurfacing Hip Replacement

This figure details the cumulative incidence of the most common reasons for revision. The five most common reasons for revision are included as long as each of these reasons account for more than 10 procedures or at least 5% of all revisions for the Durom/Durom total resurfacing hip combination. A comparative graph is provided of the cumulative incidence for the same reasons for revisions for all other total resurfacing hip prostheses.

Figure 2: Cumulative Incidence Revision Diagnosis for Primary Total Resurfacing Hip Replacement



Type of Revision Performed for Primary Total Resurfacing Hip Replacement

This analysis identifies the components used in the revision of the Durom/Durom total resurfacing hip combination and compares it to the components used in the revision of all other total resurfacing hip prostheses.

The reason this analysis is undertaken is to identify whether there is one or more components which are being replaced that differ from the components replaced for revisions of all other total resurfacing hip prostheses i.e. is there a difference in the type of revision undertaken for the Durom/Durom total resurfacing hip combination compared to all other total resurfacing hip prostheses.

Table 5: Primary Total Resurfacing Hip Replacement - Type of Revision (Follow-up Limited to 20.5 Years)

	Durom	/Durom	Other Total Resurfacing Hip		
Type of Revision	Number	Percent	Number	Percent	
THR (Femoral/Acetabular)	65	53.7	838	67.9	
Femoral Component	43	35.5	323	26.2	
Acetabular Component	4	3.3	37	3.0	
Cement Spacer	6	5.0	28	2.3	
Removal of Prostheses	3	2.5	7	0.6	
N Major	121	100.0	1233	99.8	
Head/Insert			1	0.1	
Minor Components			1	0.1	
N Minor			2	0.2	
TOTAL	121	100.0	1235	100.0	

Note: This table is restricted to revisions within 20.5 years for all groups to allow a time-matched comparison of revisions. Note: Prostheses no longer used in 2023 are excluded from the comparator.

Revision Rates of Durom/Durom Primary Total Resurfacing Hip Replacement by Fixation

This analysis is provided as some prostheses have more than one fixation option. Additionally there are prostheses where an alternative to the recommended approach to fixation was used e.g. a cementless prosthesis that has been cemented or vice-versa.

Table 6: Revised Number of Durom/Durom Primary Total Resurfacing Hip Replacement by Fixation

Fixation	N Revised	N Total
Cemented	1	2
Hybrid (Femur Cemented)	120	845
TOTAL	121	847

Revision Rates of Primary Total Resurfacing Hip Replacement by State

This enables a state by state variation to be identified for the Durom/Durom total resurfacing hip combination and provides the comparative data for each of the states for all other total resurfacing hip prostheses.

The purpose of this analysis is to determine if the higher than anticipated rate of revision has widespread distribution between states. If there is widespread distribution then the reason for the higher than anticipated rate of revision is unlikely to be surgeon specific. If the prosthesis has been used in only a small number of states it is not possible to distinguish if the higher than anticipated rate of revision is related to the prosthesis, surgeon, technique or patient.

Table 7: Revised Number of Primary Total Resurfacing Hip Replacement by State

Component	State	N Revised	N Total
Durom/Durom	NSW	51	392
	VIC	38	196
	QLD	9	83
	WA	12	103
	SA	0	3
	TAS	10	51
	ACT/NT	1	19
Other Total Resurfacing Hip	NSW	302	4184
	VIC	453	5203
	QLD	275	3966
	WA	62	1173
	SA	95	631
	TAS	1	36
	ACT/NT	57	676
TOTAL		1366	16716

Number of Revisions of Durom/Durom Primary Total Resurfacing Hip Replacement by Year of Implant

This analysis details the number of prostheses reported each year to the Registry for the Durom/Durom total resurfacing hip combination. It also provides the subsequent number of revisions of the primaries reported in that year.

Primary procedures performed in later years have had less follow up time therefore the number revised is expected to be less than the number revised in earlier years. For example, a primary procedure performed in 2023 has a maximum of one year to be revised, whereas a primary procedure performed in 2021 has a maximum of three years to be revised.

Table 8: Number of Revisions of Durom/Durom Primary Total Resurfacing Hip Replacement by Year of Implant

Year of Implant	Number Revised	Total Number
2003	12	58
2004	27	166
2005	24	207
2006	27	143
2007	15	105
2008	10	88
2009	3	46
2010	1	24
2011	2	10
TOTAL	121	847

Revision Rates of Durom/Durom Primary Total Resurfacing Hip Replacement by Catalogue Number Range

Many prostheses have a number of catalogue ranges. The catalogue range is specific to particular design features; more than one catalogue range usually indicates a minor difference in design in a particular Durom/Durom prosthesis.

This analysis has been undertaken to determine if the revision rate varies according to the catalogue number range.

Model	Catalogue Range	Catalogue Description	Cement	Material
Head				
Durom	0100211138-0100211160	METASUL RS FEMORAL COMPONENT	YES	METAL
Acetabular				
Durom	0100214044-0100214066	COCR TITANIUM PLASMA SPRAY RS ACETABULAR	NO	METAL

Table 9: Revised Number of Durom/Durom Primary Total Resurfacing Hip Replacement by Catalogue Number Range

Head Range	Acetabular Range	N Revised	N Total	
0100211138-010021116	0 0100214044-0100214066	121	847	
TOTAL		121	847	